


Infrared Dye 9684



Physical Properties – Blue free flowing powder

Melting Point = 175 °C -177°C

Lambda Max = 684 nm

Absorptivity = 123

Solubility: Chloronaphthalene.

Applications:

Laser Protective Eyewear - Block the ruby laser with excellent visible light transmission

Bandpass Filters:Very sharp cutoff at 684 nm. Can be used in Polycarbonate

Limited Availability – Please call 908-237-0300 to discuss price and availability.

Adam Gates & Company, LLC
249 Homestead Rd. Bldg 5 Unit 4
Hillsborough, NJ, 08844

Tel: (908) 829-3386
Fax: (908) 829-3387
Email:sales@adamgatescompany.com